


RENOLIT ALKORPLAN F Bright

Cool roof single ply roofing membrane



Product information

RENOLIT ALKORPLAN F Bright
Laminated membrane of flexible PVC with woven polyester reinforcing, with a highly UV reflective coating.



Certificates

Product certification EN 13956
0749-CPR / BC2-320-01452-0001-01

This product contributes to reach the best LEED, VERDE and BREEAM rating levels.
Certificates available on our website www.renolit.com/roofing.

Application

RENOLIT ALKORPLAN F Bright membrane is used as waterproofing membrane within mechanically restrained systems.

PRODUCT DATA			
	Method	Production values RENOLIT ALKORPLAN F Bright - 1,5 mm	Units
Tensile strength	EN 12311-2 (A)	≥ 1100	N/50 mm
Elongation	EN 12311-2 (A)	≥ 16	%
Dimensional stability (6h at 80 °C)	EN 1107-2	≤ 0.3	%
Cold crack temperature	EN 495-5	≤ -25	°C
Nail tear resistance	EN 12310-1	≥ 400	N
Tear resistance	EN 12310-2	≥ 225	N
Joint peel resistance	EN 12316-2	BOJ or ≥225	N/50 mm
Vapour diffusion resistance (μ)	EN 1931	20.000	-
Resistance to static perforation	EN 12730	≥ 20	kg
External fire	EN 13501-5	B _{roof} (t1), (t3) & (t4)	-
Solar reflectance	ASTM C 1549	0.91	-
SRI Solar Reflectance Index	ASTM E 1980	115	-
Surface temperature - new	ASTM E 1980	39	°C
Surface temperature after ageing	ASTM E 1980	50	°C
Accelerating weathering test after 5.000 hours of UV-A ageing	ASTM D 4434 ASTM G 154	no cracking, no crazing	-

PACKAGING					
	Thickness	Width	Weight	Roll length	Roll weight
RENOLIT ALKORPLAN F ₃₅₂₇₆	1.5 mm	1.05 m	1.85 kg/m ²	20 lm	ca. 41 kg

Storage

The rolls should be stored horizontally and parallel to each other. Store in the original packaging, in a dry and frost-free area, protected from direct sunlight. The maximum stack height in the original pallet packaging is 2 high with a protection between the pallets and 4 high in the original open crate packaging.

The RENOLIT ALKORPLAN roofing membranes are supplied in rolls on cardboard cores. Every delivery may contain up to 10% of short rolls (minimum length: 8 m).

This document replaces and supersedes all prior versions.

WWW.RENOLIT.COM/ROOFING

RENOLIT Cramlington Ltd, Station Road - Cramlington, Northumberland NE23 8AQ - United Kingdom
T +44 1670 718283 - F +44 1670 719367 - renolit.cramlington@renolit.com

RENOLIT Belgium N.V. - Export Dpt. - Industriepark De Bruwaan 43 - 9700 Oudenaarde - Belgium
T +32 (0)55 33 98 51 - F +32 (0)55 31 86 58 - renolit.belgium@renolit.com



Rely on it.