


RENOLIT ALKORPLAN D 35x76

Demarcation membrane



Product information

RENOLIT ALKORPLAN D 35x76
Synthetic roofing membrane of flexible PVC with polyester scrim reinforcement.

Application

RENOLIT ALKORPLAN D 35x76 is a membrane for the demarcation of specific zones on the roof. To be hot air welded on top of **RENOLIT ALKORPLAN** roofing membranes.

Certificates

Product certification EN 13956
0749-CPR / BC2-320-01452-0001-01

Certificate available on our website
www.renolit.alkorplan.com.

PRODUCT DATA			
	Method	Production values RENOLIT ALKORPLAN D 35x76	Unit
		1.2 mm	
Mass per unit area	EN 1849-2	1.5	kg/m ²
Tensile strength	EN 12311-2 (A)	≥1050	N/50 mm
Elongation	EN 12311-2 (A)	≥15	%
Dimensional stability (6h at 80 °C)	EN 1107-2	≤ 0.3	%
Cold crack temperature	EN 495-5	≤-25	°C
Tear resistance	EN 12310-2	≥200	N
Joint peel resistance	EN 12316-2	BOJ or ≥200	N/50 mm
Water vapour diffusion resistance (μ)	EN 1931	20,000	-
Resistance to static perforation	EN 12730	≥20	kg
Reaction to fire	EN 13501-1	E	-

PACKAGING					
	Colour	Thickness	Width	Roll length	Roll weight
RENOLIT ALKORPLAN D 35x76-007	Red (PL650)	1.2 mm	1.05 m	25 lm	ca. 42.90 kg
RENOLIT ALKORPLAN D 35x76-008	Red (PL650)	1.2 mm	0.15 m	25 lm	ca. 6.15 kg

Storage

The rolls should be stored horizontally and parallel to each other. Store in the original packaging, in a dry and frost-free area, protected from direct sunlight.

The **RENOLIT ALKORPLAN** roofing membranes are supplied in rolls on cardboard cores. Every delivery may contain up to 10% of short rolls (minimum length: 8 m).

This document replaces and supersedes all prior versions.

WWW.RENOLIT.ALKORPLAN.COM

RENOLIT Cramlington Ltd, Station Road - Cramlington, Northumberland NE23 8AQ - United Kingdom
T +44 1670 718283 - F +44 1670 719367 - renolit.cramlington@renolit.com

RENOLIT Belgium N.V. - Export Dpt. - Industriepark De Bruwaan 43 - 9700 Oudenaarde - Belgium
T +32 (0)55 33 98 51 - F +32 (0)55 31 86 58 - renolit.belgium@renolit.com

